

Mono Plast– E 305

Mono Plast – E 305

Description : Mono Plast – E 305 Super mortar , medium viscosity and solvent free .

Composition : one component product on X- Polymer system, 47 % Solid content ,

USE : Mono Plast – E 305 is a Super mortar for all Concrete surfaces , Basements and underground structures.

Excellent bonding properties to most of building material surface Non – shrink.

Preparation of surface : The surface should be free from grease and dust, very heavily oxidized surfaces should be cleaned.

Application : After thoroughly mixing component with Clean water, Mono Plast – E 305 is processed by casting.

Coverage : Depending on the surface of the substrate 1.880 - 2.050 kg of Mono Plast – E 305 Should cover between 1 square meters (one layer) 1100 microns

Color Range: Available in other color from B.C. 16 .(Shoot cartela)

Compressive Strength : > 220 / cm² .

Final Strength : After 2 - 3 days at 22 °C

Processing time : 45 minutes at 22 °C

Water Resistance : Excellent after drying.

Exterior Durability : Excellent.

Drying time : Set to touch 40 - 55 minutes , Completely Dry after 8 hours It can test after 144 hours.

Storage : To be stored for 8 months on 29°C .

Packing : Mono Plast – E 305 is supplied in 20 Kg - 25 Kg.